

LNPTM THERMOTUFTM COMPOUND VF004S

VF-1004 HS
REGION AMERICAS

DESCRIPTION

LNP THERMOTUFTM VF004S is a compound based on Super Tough Nylon resin containing 20% Glass Fiber. Added features of this material include: Heat Stabilized.

TYPICAL PROPERTY VALUES

Revision 20181231

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, brk, Type I, 5 mm/min	102	MPa	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	2.8	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	3	%	ASTM D 638
Tensile Modulus, 50 mm/min	6470	MPa	ASTM D 638
Flexural Stress, brk, 1.3 mm/min, 50 mm span	156	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	5620	MPa	ASTM D 790
Tensile Stress, break, 5 mm/min	97	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	2.6	%	ISO 527
Tensile Strain, break, 5 mm/min	3	%	ISO 527
Tensile Modulus, 1 mm/min	6000	MPa	ISO 527
Flexural Modulus, 2 mm/min	5080	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	704	J/m	ASTM D 4812
Izod Impact, notched, 23°C	128	J/m	ASTM D 256
Multiaxial Impact	6	J	ISO 6603
Instrumented Impact Total Energy, 23°C	22	J	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	42	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	12	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	256	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	240	°C	ASTM D 648
CTE, -30°C to 30°C, flow	2.99E-05	1/°C	ASTM D 696
CTE, -30°C to 30°C, xflow	8.12E-05	1/°C	ASTM D 696
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	235	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	235	°C	ISO 75/Af
PHYSICAL			
Density	1.23	g/cm ³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.74	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs	0.4 – 0.6	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs	0.8 – 1	%	ASTM D 955
Density	1.23	g/cm ³	ISO 1183
Moisture Absorption (23°C / 50% RH)	1.1	%	ISO 62
INJECTION MOLDING			

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Drying Temperature	80	°C	
Drying Time	4	hrs	
Maximum Moisture Content	0.15	%	
Melt Temperature	280 – 295	°C	
Front - Zone 3 Temperature	295 – 305	°C	
Middle - Zone 2 Temperature	275 – 290	°C	
Rear - Zone 1 Temperature	260 – 270	°C	
Mold Temperature	95 – 110	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.