

ELASTOFLEX® SA P

SELF-ADHERED GRANULATED CAP SHEET

PRODUCT DESCRIPTION

Elastoflex® SA P is a premium, granule surfaced, fire rated, self-adhered, polyester reinforced SBS modified bitumen roofing product manufactured using patented ADESO® dual-compound self-adhesive technology. A high quality elastomeric Styrene-Butadiene-Styrene (SBS) modified asphalt compound is applied on the top layer and an aggressive self-adhesive compound is applied on the bottom layer. The high performance reinforced polyester mat provides excellent dimensional stability.

The top surface of the Elastoflex® SA P membrane has a granular finish available in a variety of colors. The cap sheet features patented FASTLap® for granule free roll ends, as well as SEALLap®, a factory applied adhesive treatment at the membrane overlap. Each of these patented features provide for greater ease of application as well as improved long term weathering performance.

USES

- Designed for applications where using a propane torch is undesirable or prohibited
- New construction or approved reroofing specifications for Polyglass roofing systems or in approved flashing details
- As a flashing membrane in all applicable specifications

FEATURES AND BENEFITS

- Ease of application requiring fewer tools and eliminating time consuming application procedures
- No need for kettles, spray rigs, adhesive machines resulting in a cleaner, more environmentally friendly job site
- Excellent long-term adhesion and application to multiple substrates and base/interply membranes
- Exceptional physical properties and long-term weathering performance.
- UV stabilized long lasting granule surfacing in multiple colors

TECHNICAL DESCRIPTION

TEST METHOD	PROPERTY	ASTM VALUE
ASTM D5147	Peak Load @ 23+/-2°C (73.4+/-3.6°F), MD and XMD, min, kN/m (lbf/in.)	8.8 (50)
ASTM D5147	Elongation @ 23+/-2°C (73.4+/-3.6°F), MD and XMD, min (%)	35
ASTM D5147	Tear Strength @ 23+/-2°C (73.4+/-3.6°F), min, N (lbf)	246 (55)
ASTM D5147	Low Temperature Flexibility, max, °C (°F)	-18 (0)
ASTM D5147	Granule Embedment, max, g	2
ASTM D1970	Adhesion to Plywood @ 40°F, min, lbf/ft width	2.0
ASTM D1970	Adhesion to Plywood @ 75°F, min, lbf/ft width	12.0
ASTM D1970	Sealability around nail	pass
ASTM D1970	Waterproof integrity after low temp flexibility	pass
ASTM D1970	Waterproof integrity of lap seam	pass

AVAILABLE COLORS

Top surface granule protection is available in a variety of colors such as:

Black Buff Chestnut Grey Slate Oak
 White Red Blend Pine Green Heather Blend Weatherwood



PRODUCT DATA

Coverage (Approx) 100 sq ft
 Weight (Approx) 90 lbs
 Thickness (Nominal) 3.5 mm; 140 mils
 Roll Size 32'10" x 39 3/8" (10m x 1m)
 Rolls/Pallet 20

APPLICABLE STANDARDS

- ASTM D6164 Type I
- Miami Dade Code Compliance
- Factory Mutual Approved
- UL Classified for use in class A, B or C roofs, as listed the latest UL "Roofing Materials and Systems Directory"
- ICC ESR-2018
- Florida Building Code
- TDI



PRODUCT WARRANTY

Polyglass U.S.A., Inc. commercial roofing membranes can be backed with a manufacturer's warranty for up to 20 years when used as part of an approved, multi-ply roofing system. Please see your Polyglass U.S.A., Inc. Sales or Technical Representative for specifications and details.



www.polyglass.us

ADESO PRODUCTS

ELASTOFLEX® SA P

SELF-ADHERED GRANULATED CAP SHEET

APPLICATION INSTRUCTIONS

Elastoflex SA P is intended to be used as a cap sheet for new or re-roof applications as part of a multi-ply system when applied to acceptable insulations and/or coverboards for commercial and residential structures. Elastoflex SA P may also be applied directly to approved wood deck substrates of non-occupied spaces such as carports, sheds, canopies, etc.

- Apply only when the weather and forecast is dry and the ambient air temperature and substrate is 40°F (5°C) and rising.
- Apply over clean, dry, dust and debris-free substrates. Prime concrete decks prior to application with PG 100 Asphalt Primer.
- When re-roofing, remove all prior roofing materials down to a clean debris-free substrate and properly close-off all abandoned roof penetrations.
- Concrete or steel decks shall be designed with proper expansion devices.
- Wood decks shall have all joints blocked and properly supported.
- Ensure the installation of Elastoflex SA P does not prevent the ventilation of existing construction.
- Do not apply over shingles or other granulated surface.
- While installing Elastoflex SA P:
 1. Start at the low point of the roof.
 2. Unroll the material and allow to relax.
 3. Start by removing the first 18-24" of release film.
 4. Press the membrane into place with firm and even pressure. Roll the edges with a silicone hand roller to ensure complete adhesion.
 5. Gradually remove the remaining release film applying pressure from the center to the edges as you go.
 6. Position successive rolls providing a minimum 6" end lap and 4" side lap. Laps can be sealed for additional water tightness with a hot air welder.
 7. After installation of the entire roof surface, roll with an 80# split-face linoleum roller. Take care on sloped roofs by securing the roller and applicator with the appropriate safety equipment.
- Details and flashing may be installed using Elastoflex SA P with a hot air welder or with PG 500 Roof Cement. Check project details for proper installation requirements.

POLYGLASS U.S.A., INC. MANUFACTURING FACILITIES

- Fernley, NV
- Hazleton, PA
- Winter Haven, FL

CORPORATE HEADQUARTERS

Polyglass U.S.A., Inc.
1111 West Newport Center Drive
Deerfield Beach, FL 33442
www.polyglass.us

General Line: (888) 410-1375
(954) 233-1330

Customer Service: (800) 222-9782

Technical Service: (866) 802-8017

Questions? technical@polyglass.com

Product Disclaimer: Unless otherwise incorporated into or part of a supplemental manufacturer's warranty, Polyglass warrants its product(s) against manufacturing defects in its product that directly results in leakage for a period of 5 years.

Refer to material safety data sheet (MSDS) for specific data and handling of our products. All data furnished refers to standard production and is given in good faith within the applicable manufacturing and testing tolerances.

Polyglass U.S.A., Inc., reserves the right to improve and change its products at any time without prior notice. Polyglass U.S.A., Inc. cannot be held responsible for the use of its products under conditions beyond its own control.

For most current product data and warranty information, visit www.polyglass.us

Copyright ©2015 by Polyglass U.S.A., Inc. and all rights are reserved
Edition Date: 2/15 • Doc# Elastoflex SA P



www.polyglass.us